



Product Specifications

Slow Recovery PVC Foam

Description: A closed-cell, medium density, polyvinyl chloride (PVC) foam that conforms to shapes under pressure, yet exhibits slow but full recovery from compression.

<u>Characteristic</u>	<u>Method</u>	<u>Target</u>	<u>Tolerance</u>
Density	ASTM D-1667	14 lbs/ft ³	± 2 lbs/ft ³
25% Compression Set (Max%) Based on original height	ASTM D-1667	≤ 8.0%	
Tensile Strength (PSI)	ASTM D-412	75, min	
Hardness (Shore 00)	ASTM D-2240	55	± 5
Color	Custom colors available		

Certified by Ludlow Composites lab

Specifications are subject to revision.

Ludlow Composites Corporation

2100 Commerce Drive, Fremont, Ohio 43420 (419) 332-5531